

GA-30*3 series heat cure rubber

30-70 shore hardness, DBPMH, high resilience fumed silicone rubber

Feature

- Good resilience property
- Excellent processability property

Application

- High-grade sealings
- Placemat

Meet LFGB

• Sprot seat

Typical characteristics

Product code	GA-3033	GA-3043	GA-3053	GA-3063	GA-3073
Appearance	Transparent				
William plasticity	140	180	200	230	260
Hardness(ShoreA)	30	40	50	60	70
Density(g/cm3)	1.08	1.1	1.13	1.16	1.18
Tensile strength(Mpa)	5.5	9	9	9	8.5
Elongation(%)	550	500	400	300	200
Tear strength(KN/m)	12	20	20	20	20

Remark:

1.The above data obtained from testing by using 1.0% of peroxide (DBPMH) in pressurized solidification for 5 minutes at 175 °C to make a 2 mm thickness specimen. 2.The above data is not for specification customized, before make this product specification, please contact genvan sales person.

Description

GA-30*3series products have good resilience,small deformation,excellent processability;products contact with food need to do two-process treatment at 200°C 4hours.

Package

The product by standard measurement, plastic film packaging, for 20kgs/ box.Samples available.



深圳市正安有机硅材料有限公司 Shenzhen genvan silicone materails co.,ltd 东莞市正安有机硅科技有限公司 Dongguan genvan silicone technology co.,ltd

Application, coloring, modifying, mixing

Products can be colored to maintain the color of the pigment itself; Can use genvan' s additive to the properties, like aging resistance, compression deformation of the product, more detailed info. for how to use the additives, please contact Genvan company local sales or customer service.

Storage&period of validity

The product is stored unopened at 50°C or below the shelf life is 6 months from the date of production; Out of the expiration date, it shall be fully tested. Determine to meet the customer's own product specifications, only continue to use.

Product safety info.

This information does not include safety info. for how to use this product safely.

Please read product, safety data sheet, labels on product packing container before operation.

For safety data sheet, can log in <u>www.genvan.com</u> to download or obtain from Genvan company sales person.

Limited warranty information - please read carefully

◆Based on the premise of good faith, provided here information should be considered accurate.However,Due to the condition and method of using our company product is beyond our control. This information can not replace the relevanted testing from customer to assure our company product safety, effective,and fully meet final application.The using suggestions we offered ,can not be deemed to infringe any patent right's reason.

♦Genvan's only guarantee is the company's products in all the necessary tests were carried out before shipment the test data conform to the factory standard.

Genvan emphasizes that no any promise of compensation for any indirection or attachment damage incurred.

◆Due to different testing production conditions, we cannot make sure we both get the same test results users are advised to use their own testing conditions to get the data as the using performance properties.

◆Any of the above performance data and applicable recommendations, only is one of use references for the performance of Genvan products instead of the guarantee for the effectiveness or universality of Genvan products in a particular application.

♦We reserve the right to change the parameters of the product without further notice.